

SILICONE FLUIDS

Description

Basildon Chemicals Dimethyl Silicone Fluids known chemically as polydimethylsiloxanes, are available in various viscosities ranging from 0.65cS to 60,000cS. They are clear, non-toxic, inert and odourless fluids.

Product Features

1. Low viscosity — temperature change.
2. Wide operational temperature range.
3. Excellent thermal stability.
4. Chemically inert to most materials.
5. Low surface tensions.
6. High compressibility.
7. High shear stability.
8. Excellent heat conductivity.
9. Excellent dielectric properties.
10. Non-corrosive.

Typical Properties

These values are not intended for use in preparing specifications (see table).

Please note that other viscosities may be available - contact our Sales Department for further details.

Applications

BC Dimethyl Silicone Fluids are recommended for a wide variety of industrial

applications. For example in polishes and cosmetics, as antifoam additives in paint and printing inks, in dashpots and damping devices, as liquid dielectrics and as antifoams in lube oils.

Toxicity and Handling

Polydimethylsiloxane fluids have a very low order of toxicity and if handled with reasonable care present negligible skin irritation problems. Direct contact of the fluid with the eyes may cause slight irritation. See our Health and Safety sheet for more information.

Storage and Shelf Life

Shelf life of the unopened container is 24 months from date of manufacture. If you wish to use the product after this time please contact us for approval.

Technical Service

Our technical and sales staff have considerable experience of the use of silicone products in a very wide variety of industries and the benefit of this experience is freely available to all our customers.

Basildon Chemical Company Limited

Kimber Road, Abingdon, Oxon, OX14 1RZ Telephone: 81044 (1235)526677

Facsimile: 44 (1235)524334 Web-Site: www.baschem.co.uk E-mail: Sales@baschem.co.uk

Typical Properties

Nominal Viscosity at 25°C	Viscosity Temperature Coefficient	Specific Gravity 25°C	Refractive Index at 25°C	Pour Point °C	Flash Point °C	Surface Tension dynes/cm at 25°C	cS
0.65	0.31	0.760	1.375	-	-4	15.9	
5	0.53	0.916	1.397	-100	135	19.7	
10	0.56	0.934	1.399	-100	163	20.1	
20	0.58	0.953	1.401	-84	232	20.8	
50	0.59	0.963	1.402	-70	285	20.8	
100	0.59	0.968	1.4040	-65	315	20.9	
200	0.59	0.972	1.4031	-65	315	21.0	
350	0.60	0.973	1.4032	-65	315	21.1	
500	0.60	0.973	1.4033	-50	315	21.1	
1,000	0.60	0.974	1.4035	-50	321	21.1	
12,500	0.60	0.975	1.4035	-46	321	21.3	
30,000	0.60	0.976	1.4035	-43	321	21.3	
60,000	0.60	0.977	1.4035	-41	321	21.3	

Although every effort has been made to ensure that the information contained in this data sheet is reliable, we cannot be held responsible for the correctness of the information or for any loss, injury or damage which may result from its use. Also suggestions of uses should not be taken as inducements to infringe any particular patent.

June 2001

AUTOMOTIVE AND HOUSEHOLD PRODUCTS