

**Guide Formulation**

POL15

**Creamed Wax Polish**

<b>Raw Material</b>	<b>% Weight</b>
Hoechst Wax S <sup>1</sup>	5.88
Oleic acid	0.90
AMP 95 <sup>2</sup>	0.72
White Spirit	43.40
Soft water	34.60
BC 200cS <sup>3</sup>	4.40
BC 93/074 Aminofunctional Silicone Fluid <sup>3</sup>	1.00
Speswhite <sup>4</sup>	9.10

**Supplier**

- <sup>1</sup> Hoechst
- <sup>2</sup> Angus Chemicals
- <sup>3</sup> Basildon Chemicals
- <sup>4</sup> ECC International

**Method**

- Charge wax and white spirit, heat until a clear solution is obtained.
- Add Oleic acid, AMP95 and BC 93/074 and BC 200cS fluid.
- Mix Speswhite with soft water.
- Add Speswhite blend to with constant stirring at high speed. Continue to mix for 20-30 minutes after final addition.

*Basildon Chemical Company Limited ("the Company") has supplied the above formulation to you only as a guide. It is important to note that the formulation provided above is not a commercial formulation and has not been tested by the Company. The formulation must be evaluated and modified by you for your own requirements before use and the Company hereby excludes all and any liability to you or any third party user for any losses or damages incurred as a result of use of the formulation as provided above, to the fullest extent permitted by law. Under no circumstances shall the Company be liable to you or any third party user for consequential losses such as loss of earnings, loss of profits, loss of reputation and the like.*