

Guide Formulation

POL3

Solvent Based Tyre Dressing

Raw Material	% Weight
BC 60,000cS	4.0
BC 350cS	16.00
BC 93/074	0.5
Solvent (White spirit, kerosene or similar)	79.5

Supplier

Basildon Chemicals

Method

- Disperse the BC ingredients in the solvent with continuous mixing.

Basildon Chemical Company Limited ("the Company") has supplied the above formulation to you only as a guide. It is important to note that the formulation provided above is not a commercial formulation and has not been tested by the Company. The formulation must be evaluated and modified by you for your own requirements before use and the Company hereby excludes all and any liability to you or any third party user for any losses or damages incurred as a result of use of the formulation as provided above, to the fullest extent permitted by law. Under no circumstances shall the Company be liable to you or any third party user for consequential losses such as loss of earnings, loss of profits, loss of reputation and the like.