

Guide Formulation

POL9

**Detergent Resistant
Wax Free Polish**

Raw Material	% Weight
A Water (soft)	60.32
Preservative	0.21
Speswhite ¹	9.42
Softanol 90 ²	0.75
B White Spirit	18.22
Pemulen 1622 ³	0.16
BC 50cS Silicone Fluid ⁴	3.02
BC 1000cS Silicone Fluid ⁴	1.02
C AMP ⁵	0.82
Soft water	1.00
D BC 93/074 Amino Silicone Fluid ⁴	2.37
White Spirit	2.69

Supplier

- ¹ ECC International
- ² Honeywell & Stein
- ³ BF Goodrich
- ⁴ Basildon Chemicals
- ⁵ Angus Chemicals

Method

- Mix components of A under high shear.
- Mix components of B and add to A.
- Mix components of C and add to (A+B).
- Mix components of D and add to (A+B+C).

Basildon Chemical Company Limited ("the Company") has supplied the above formulation to you only as a guide. It is important to note that the formulation provided above is not a commercial formulation and has not been tested by the Company. The formulation must be evaluated and modified by you for your own requirements before use and the Company hereby excludes all and any liability to you or any third party user for any losses or damages incurred as a result of use of the formulation as provided above, to the fullest extent permitted by law. Under no circumstances shall the Company be liable to you or any third party user for consequential losses such as loss of earnings, loss of profits, loss of reputation and the like.